Seamless EO steel tubes Material E235N (St. 37.4)

Tolerances DIN EN 10305-4

Order code						Design pressure bar			
Phosphated and oiled	Cr(VI)-free	Tube O.D. (mm)	Tolerance	Wall thickness (mm)	Tube I.D. (mm)	DIN 2413 I Static	DIN 2413 III Dynamic	Burst pressure bar	Weight kg/m
R04X0.5	**R04X0.5CF**	4		0.50	3.0	313	273	1160	0.047
	R04X0.75CF	4	±0.08	0.75	2.5	470	391	1820	0.063
R04X1	**R04X1CF**	4		1.00	2.0	627	500	2700	0.074
	R05X1CF	5	±0.08	1.00	3.0	501	416	2120	0.099
	R06X0.75CF	6		0.75	4.5	333	288	1150	0.103
R06X1	**R06X1CF**	6		1.00	4.0	444	372	1650	0.123
R06X1.5	**R06X1.5CF**	6	±0.08	1.50	3.0	666	526	2550	0.166
	R06X2CF	6		2.00	2.0	692	662	>3500	0.197
	R06X2.25CF	6		2.25	1.5	757	725	>3500	0.208
R08X1	**R08X1CF**	8		1.00	6.0	333	288	1175	0.173
R08X1.5	**R08X1.5CF**	8	±0.08	1.50	5.0	499	412	1925	0.240
R08X2	**R08X2CF**	8		2.00	4.0	666	526	2500	0.296
	R08X2.5CF	8		2.50	3.0	658	630	2650	0.339
R10X1	**R10X1CF**	10		1.00	8.0	282	248	900	0.222
R10X1.5	**R10X1.5CF**	10		1.50	7.0	423	357	1450	0.314
R10X2	**R10X2CF**	10	±0.08	2.00	6.0	564	458	2025	0.395
	R10X2.5CF	10		2.50	5.0	705	551	2675	0.462
	R10X3CF	10		3.00	4.0	666	638	>3500	0.518
R12X1	**R12X1CF**	12		1.00	10.0	235	209	750	0.271
R12X1.5	**R12X1.5CF**	12		1.50	9.0	353	303	1150	0.388
R12X2	**R12X2CF**	12	±0.08	2.00	8.0	470	391	1600	0.493
	R12X2.5CF	12		2.50	7.0	588	474	2025	0.586
	R12X3CF	12		3.00	6.0	705	551	2600	0.666
	R12X3.5CF	12		3.50	5.0	651	624		0.734
	R14X1.5CF	14		1.50	11.0	302	264	975	0.462
R14X2	**R14X2CF**	14		2.00	10.0	403	342	1325	0.592
	R14X2.5CF	14	±0.08	2.50	9.0	504	415	1650	0.709
R14X3	**R14X3CF**	14		3.00	8.0	604	485	2200	0.814
		14		3.50	7.0	705	551	2625	0.906
R15X1	**R15X1CF**	15		1.00	13.0	188	170	575	0.345
R15X1.5	**R15X1.5CF**	15		1.50	12.0	282	248	950	0.499
R15X2	**R15X2CF**	15	±0.08	2.00	11.0	376	321	1275	0.641
		15		3.00	9.0	564	458	2000	0.888
R16X1.5	**R16X1.5CF**	16		1.50	13.0	264	233	850	0.536
R16X2	**R16X2CF**	16	±0.08	2.00	12.0	353	303	1175	0.691
R16X2.5	**R16X2.5CF**	16		2.50	11.0	441	370	1500	0.832
R16X3	**R16X3CF**	16		3.00	10.0	529	433	1850	0.962
R18X1	**R18X1CF**	18		1.00	16.0	157	143	450	0.419
R18X1.5	**R18X1.5CF**	18		1.50	15.0	235	209	700	0.610
R18X2	**R18X2CF**	18	±0.08	2.00	14.0	313	273	975	0.789
R18X2.5	**R18X2.5CF**	18		2.50	13.0	392	333	1300	0.956
	R18X3CF	18		3.00	12.0	470	391	1575	1.111

Surface finish:
- Phosphated and oiled:
- Tubes with I.D. 1.5–5 mm: outside and inside oiled.
- Tubes from 6 mm I.D.: outside and inside phosphated and oiled.
- Cr(VI)-free:
  These dimensions are externally thick coat passivated (thickness of coat 8–12 µm), inside oiled.

Calculation pressures:

Calculation pressures given are according to DIN 2413 part I for **static stress**

$$P = \frac{20 \cdot K \cdot s \cdot c}{S \cdot d_a} \text{ (bar)}$$

Material characteristic value K = 235N/mm² and DIN 2413 part III for **dynamic stress**

$$P = \frac{20 \cdot K \cdot s \cdot c}{S \cdot (da + s \cdot c)} \text{ (bar)}$$

Material characteristic value K = 226 N/mm² (permanent fatigue strength)

Safety correction value S = 1.5 for static and dynamic stress, S = wallthickness.
Factor c for consideration of wall thickness divergence **for static and dynamic stress** = 0.8 for tube O.D. 4 and 5; 0.85 for tube o.d. 6 and 8; 0.9 for larger tube O.D.